

E - PVC PLANT

Parameter Unit	K-Value	Sieve Analysis >63 µm (%)	Volatile Matter (%)	Methanol Extract (%)	Thermostability ^(min) Mathis Drying Oven	Paste Viscosity 1h (Pas)	Residual VCM (ppm)	
Test Method	DIN	53726	53724	7764/2	53738	Vinnolit THMA 180	DIN EN 11468 PVC/DOP=100/60	53743
	ISO	1628/2	565	1269	6472	-----	DIN EN 3219 32°C, 16sec ⁻¹	6401
E 60	59-61	≤1.5	≤0.3	<2.5	≥15	≤13	≤1	
E 6644	64-66	≤1.5	≤0.3	<2	≥15	≤7	≤1	
E 6834	67-69	≤2	≤0.3	<2.5	≥15	≤6	≤2	
E 7044	69-71	≤2	≤0.3	<2	≥15	≤7	≤1	
E 7244	71-73	≤1.5	≤0.3	<2.5	≥20	≤5	≤1	
E 7544	74-76	≤1.5	≤0.3	<2.5	≥20	≤5	≤1	

PRODUCTS


MAIN FIELDS OF APPLICATION FOR PRODUCT

- E 60** Paste grade for well covering
- E 6644** Paste grade for leather foam, wall covering, cushion floor
- E 6834** Paste grade for rigid foam for flooring, leather cloth, sealing compounds, coating & laminating
- E 7044** Paste grade for leather skin, gloves, leather cloth, wall covering
- E 7244** Paste grade for wall covering, gloves, toys, cushion floor, leather cloth, book binding
- E 7544** Paste grade for leather skin, metal coating, molding, wall covering, gloves, marking films

S - PVC PLANT

Parameter Unit	K-Value	Viscosity Number	Bulk Density (g/l)	Sieve Analysis (%)		Retained on 0.4 mm sieve (mm)	Porosity (Plasticiser Absorption) (%)	Volatile Matter	Flowability (g/150g) (10 m m nozzle)	Residual VCM (ppm)	Dark Resin Particles	Fish Eye	Sulfate ash
				>63 µm (%)	>250 µm (%)								
Test Method	DIN		60						53743	Vinnolit F5	Vinnolit H1		
	ISO	1628-2	1682-2	60	4610	4610	4610	4608	1269	6186	6401	In powder	Feltest Per 25cm ²
S 5831	58±1	82	540-600	95-100	0-1	<1	14-20	<0.3	≤25	≤1	≤20	≤5	≤0.1
S 6031	60±1	87	520-580	95-100	0-1	<1	16-22	<0.3	≤25	≤1	≤20	≤5	≤0.1
S 6532	65±1	105	550-610	95-100	0-5	<1	19-25	<0.3	≤25	≤1	≤20	≤20	≤0.1
S 6732	67±1	113	550-610	95-100	0-5	<1	18-24	<0.3	≤25	≤1	≤20	≤20	≤0.1
S 6542	65±1	105	460-520	95-100	0-1	<1	24-30	<0.3	≤35	≤1	≤20	≤2	≤0.1
S 7042	70±1	125	450-510	95-100	0-1	<1	29-35	<0.3	≤35	≤1	≤20	≤2	≤0.1
S 7242	72±1	128-136	430-490	95-100	0-1	<1	30-35	<0.3	≤35	≤1	≤10	≤2	≤0.1
S 8040	80±1	164-172	420-480	95-100	0-1	<1	30-35	<0.3	≤35	≤1	≤10	≤2	≤0.1

ARVAND PETROCHEMICAL



- S 5831** K-value 58, for rigid films, bottles, fittings & injection moulded parts
- S 6031** K-value 60, for rigid & semi-rigid profiles & sheets
- S 6532** K-value 65, standard grade for rigid & semi-rigid & plasticized PVC; pipes, profiles, tubes, sheets & film
- S 6732** K-value 67, standard grade for rigid & semi-rigid & plasticized PVC; pipes, profiles, tubes, sheets & film
- S 6542** K-value 65, standard grade for semi-rigid & plasticized profiles, films & flexible articles
- S 7042** K-value 70, for plasticized profiles, cable insulation, injection molded parts, shoe soles
- S 7242** K-value 72, plasticized film & profiles, injection molded parts medical tubes & medical gloves
- S 8040** K-value 80, plasticized film & profiles, sealings, blood bags & medical tubes

اروند

پتروشیمی

پتروشیمی اروند سرامتی گرامد و خلایق با سودآوری پایدار در آقی ۱۴۰۵



دفتر تهران
میدان هفت تیر، ابتدای خیابان کریم خان زند، پلاک ۴۶، طبقه نهم
تلفن: ۰۲۱ - ۸۸ ۳۱ ۰۶ ۵۳ - ۴
تلفن: ۰۲۱ - ۸۸ ۳۱ ۰۶ ۵۵

دفتر مرکزی
استان خوزستان، بندرماهشهر، منطقه ویژه اقتصادی پتروشیمی، سایت سه
تلفن: ۰۲۱ - ۵۲ ۱۲ ۶۴ ۰۱ - ۲
تلفن: ۵۲ ۱۲ ۶۴ ۰۰

www.arvandpvc.ir
info@arvandpvc.ir
arvand.pvc

